



CONVERSION DE GRAMOS A MILILITROS

RELACION DE MEZCLA 100 : 50 : 30



REGLA # 1



100



50



30

TOTAL MEZCLA ML	AUTOCLEAR III		HARDENER STD		ACTIVADOR	
	GRS.	ML	GRS.	ML	GRS.	ML
18	10.2	10	5.1	5	2.7	3
36	20.3	20	10.2	10	5.4	6
54	30.5	30	15.4	15	8.1	9
72	40.6	40	20.5	20	10.8	12
90	50.8	50	25.6	25	13.5	15
108	61.0	60	30.7	30	16.2	18
126	71.1	70	35.9	35	18.9	21
144	81.3	80	41.0	40	21.6	24
162	91.4	90	46.1	45	24.3	27
180	101.6	100	51.2	50	27.0	30
270	152.4	150	76.9	75	40.5	45
360	203.2	200	102.5	100	54.0	60
450	254.0	250	128.1	125	67.4	75
540	304.8	300	153.7	150	81.0	90
630	355.6	350	179.4	175	94.4	105
720	355.4	400	205.0	200	108.0	120
810	456.2	450	230.6	225	121.4	135
900	507.0	500	256.2	250	135.0	150

Nota: Sera importante la exactitud de peso en cada uno de los componentes
 Recuerde mezclar al adicionar cada producto

Transparente + Hardener



+ Activador

